


SAMHARD®

FLOOR HARDENER (METALLIC)



Interior application



Heavy traffic areas



High compressive strength

DESCRIPTION:

- SAMHARD® consists of special hard-wearing aggregates which have been selected for their physical properties of abrasion and wear-resistance as well as shape and size.

ADVANTAGES:

- A metallic compound, yet it is non-rusting.
- Hard wearing aggregates provide properties of abrasion and wear-resistant hard surface.
- Provides a dense, non-porous surface.
- Forms monolithic bond with base concrete.
- Resistant to oils and greases.

PROPERTIES:

- Improves the abrasion resistance of concrete by 225%.
- Ensures minimum compressive strength of 700 kg/cm²
- Light reflection is 30% more.

METHOD OF USE:

- To be applied in two application stages.
- SAMHARD® is evenly broadcast onto the concrete surface when the material becomes uniformly dark by absorption of moisture from the concrete. Thereafter the first application can be floated.
- After floating, immediately SAMHARD® is again thrown evenly over the surface. Once moisture is absorbed, the surface can be floated in the same way as before.

RECOMMENDED APPLICATIONS:

- Industrial areas subjected to heaviest traffic like loading bays, trucking lanes, car parks, workshops, machine shops, ramps and spillways etc.
- Industrial flooring in areas like breweries, food processing, dairies, tanneries, power stations, chemical refineries, metal plating, aircraft hangers, hospitals, laboratories etc.

PRODUCT DATA:

Form	Powder
Base	Cement
Bulk density	2100 kg/m ³
Chloride content	Nil
Colour	Grey, brick red and natural
Coverage / Consumption	Light traffic : 3.0 kg/sq. mt Medium traffic : 5.0 kg/sq. mt Heavy traffic : 7.0 kg/sq. mt
Shelf life	12 months at 25°C
Safety	Non-toxic, non-flammable
Packing	25 kgs in HDPE bag

CONSULT OUR PRODUCT APPLICATION DEPARTMENT (PAD) IN CASE OF ANY DIFFICULTY OR FOR TECHNICAL ASSISTANCE

SAMROCK products are guaranteed for the performance of material and manufacture.
The details given here are based on our laboratory and field observations and as such as construed to be reliable. But we shall not accept responsibility for any work carried out with our material as we do not have control over other ingredients, workmanship and field conditions. This data sheet is subject to change in view of constant research and development being undertaken in our laboratories. Customers are advised to contact SAMROCK for the latest version.

SAMROCK CHEMICALS (I) LTD.

ISO : 9001 Company | CIN No. : U24231GJ1991PLC015607

302, Chanakya Building, Near Dinesh Hall, Ashram Road, Ahmedabad, Gujarat - 380009

Call : +91 9825011576 | Email : info@samrockchem.com