


SAMTILE® AM-3

TILE ADHESIVE FOR EXTENDED OPERATIVE & SLIP

RESISTANCE (CONFORMS TO IS 15477:2019, TYPE 3, T)



DESCRIPTION:

- SAMTILE® AM-3 is a high strength adhesive and is suitable for tiles and stone-tiles of any size on exterior wall substrates, like plaster and concrete. It is used in thin bed method for installation of all types of tiles and natural stone-tiles.
- This adhesive is used mainly for tiles and stone-tiles which are included in Type 1 and Type 2 adhesives, but is with enhanced properties of Slip Resistance and Extended Open Time necessary for fixing large tiles and stones mostly on concrete and plaster surface in interior and exterior applications. It conforms to all the parameters of IS (BIS) Type 3 Adhesive.

METHOD OF APPLICATION:

- Take the entire pack of 20-kg SAMTILE® AM-3. Add 4.5 liters to 5 liters of water and mix properly with a mixing machine.
- Apply it on the substrate with a square-notch trowel in thin-bed method for installation of all types of tiles and natural stone-tiles.
- Substrates like plaster and concrete should be dust-free and saturated with water.

RECOMMENDED APPLICATIONS:

- SAMTILE® AM-3 is used for laying all types and formats of Ceramic, Vitrified, Clay Bricks, Basalt, Glass-Mosaic and Porcelain Tiles and natural stone-tiles.

PACKING DETAILS:

- 20-kg HDPE bags

TECHNICAL DATA:

Appearance	Grey / white ready-mixed
Water required for SAMTILE® AM-3 grey / white	4.5 liters to 5 liters per bag of 20-kg
Temperature range for application	5 - 35°C
Bed thickness obtainable	2-15mm
Open time	Not less than 30 minutes
Adjustability	Not less than 25 minutes
Foot traffic	≈ 24 hours
Grouting	≈ 8 h on wall and ≈ 24 h on floor
Interval before normal use	≈ 7 days
Coverage	1.2 kg/m ²
Pot life	Approximately 3 hours
Shelf life	12 months in the original packaging in dry environment

FINAL CHARACTERISTICS:

Tensile adhesion after 28 days	Dry condition: ≥ 1.5 N/mm ² Wet condition: ≥ 1.0 N/mm ²
Shear adhesion after 28 days	Dry condition: ≥ 1.5 N/mm ² Heat aging condition: ≥ 1.0 N/mm ² Wet condition: ≥ 1.0 N/mm ²

CONSULT OUR PRODUCT APPLICATION DEPARTMENT (PAD) IN CASE OF ANY DIFFICULTY OR FOR TECHNICAL ASSISTANCE

SAMROCK products are guaranteed for the performance of material and manufacture.
The details given here are based on our laboratory and field observations and as such as construed to be reliable. But we shall not accept responsibility for any work carried out with our material as we do not have control over other ingredients, workmanship and field conditions. This data sheet is subject to change in view of constant research and development being undertaken in our laboratories. Customers are advised to contact SAMROCK for the latest version.

SAMROCK CHEMICALS (I) LTD.

ISO : 9001 Company | CIN No. : U24231GJ1991PLC015607

302, Chanakya Building, Near Dinesh Hall, Ashram Road, Ahmedabad, Gujarat - 380009

Call : +91 9825011576 | Email : info@samrockchem.com