


SAMCRETE® GP

GROUT (CEMENT-BASED) (GENERAL PURPOSE)



2/3 components



Brush application

DESCRIPTION:

- SAMCRETE® GP (General Purpose) Grout (Cement-based) renders durable and trouble-free foundation for industrial machinery and other grouting needs. It is a design mix of portland cement, graded fillers and chosen chemical additives to impart strength and flow and also to compensate dual shrinkage and to ensure effective contact and support.

GENERAL SPECIFICATIONS:

- **Grain size :** 0-2 mm
- **Water content (%) :** 13-15
- **Linear expansion (maximum %) :**
 Free: 2.0
 Restrained: 1.2
- **Yield (50 kgs dry grout) :** 25 litres slurry

ADVANTAGES:

- Gaseous expansion system compensates for shrinkage problems and maintains its original volume during curing.
- Control expansion ensures surface contact after setting.
- Develops exceptionally high ultimate strength combined with dense impermeable structure.
- Provides trouble-free performance.
- Facilitates rapid installation and early operation of plant.
- No metallic iron content to corrode and cause staining or deterioration due to rust expansion. This grout also imparts high frost, fire and oil resistance.

METHOD OF USE:

- Mix dry grout with recommended quantity of water for minimum 3 minutes.
- Water quantity per bag of 25-kg grout:

Flowable: 4.5 litres
 Trowellable: 4.1 litres



RECOMMENDED APPLICATIONS:

- Industrial machinery foundations
- Drill holes in rock and concrete structures
- Stabilization of rock structures and embankments
- Anchoring of bridge bearings etc.
- Base Plate grouting of steel stanchions, steel trusses etc.

SAMCRETE® GP is recommended for general purpose medium and heavy machinery foundations with static loads. It is also recommended for use in heavy machinery foundations with dynamic loads as well as other special applications.

Special grades of **SAMCRETE® GP** can also be designed to suit specific needs of special applications.

SAMCRETE® GP is extensively used for the following:

Boilers * Process line equipments for industries
D G Sets * Chemicals * Textiles
Compressors * Petrochemicals * Paper
Pumps * Plastics * Steel
Furnaces * Engineering industry * Mining * Minerals
Cranes * Rubber & Tyres * Electrical & Electronics
Drilling platforms * Agro industry * Automobiles * Glass
Turbines * Fertilizers * Power sector

It is recommended not to mix grout with concrete admixtures.
Also recommend not to batch-grout by fraction of a bag.

CONSULT OUR PRODUCT APPLICATION DEPARTMENT (PAD) IN CASE OF ANY DIFFICULTY OR FOR TECHNICAL ASSISTANCE

SAMROCK products are guaranteed for the performance of material and manufacture.
The details given here are based on our laboratory and field observations and as such as construed to be reliable. But we shall not accept responsibility for any work carried out with our material as we do not have control over other ingredients, workmanship and field conditions. This data sheet is subject to change in view of constant research and development being undertaken in our laboratories. Customers are advised to contact SAMROCK for the latest version.

SAMROCK CHEMICALS (i) LTD.

ISO No : 9001 | CIN No. : U24231GJ1991PLC015607

302, Chanakya Building, Near Dinesh Hall, Ashram Road, Ahmedabad, Gujarat - 380009

Call : +91 9825011576 | Email : info@samrockchem.com

PRODUCT DATA:

Form	Powder-grain mix (fillers)										
Base	Cement										
Bulk density	2170 kg/m ³										
Chloride content	Nil (chloride-free)										
Colour	Grey										
Curing	7 days (minimum)										
Compressive strength (N/mm²) (IS 516-1959) W/P ratio 0.18	<table border="1"> <thead> <tr> <th>Age (days)</th> <th>Flowable</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>12</td> </tr> <tr> <td>3</td> <td>29</td> </tr> <tr> <td>7</td> <td>37</td> </tr> <tr> <td>28</td> <td>50</td> </tr> </tbody> </table> <p>Note: Cubes cast were kept under restraint before testing to simulate site condition. Size of the cubes used was 70.6 x 70.6mm x 70.6mm and tested at 3000C.</p>	Age (days)	Flowable	1	12	3	29	7	37	28	50
Age (days)	Flowable										
1	12										
3	29										
7	37										
28	50										
Caution	Restrict mixing to quantities, which can be placed in 10 to 15 minutes										
Storage	In dry and close place										
Young's modulus	24 KN/mm ²										
Thermal conductivity	1.04 W/m°C										
Safety	Non-toxic and non-flammable										
Packing	25 kg HDPE bags										

SURFACE PREPARATION:

- Clean the concrete base (like bolt pocket) of dirt, debris, oil and grease etc.
- Wet the surface thoroughly.
- Remove all excess and free water.

PLACEMENT:

- Place or pour grout mix quickly and continuously through holes or from one side only.
- Spread and compact by rodding, only if required.
- Do not place or pour grout from two or more sides for good ensured quality.
- In order to minimize heat build-up in thicker sections, it is recommended to add up to 50% well graded silt-free 10mm aggregate.

CURING:

- Curing should be started immediately after 6 hours from the time of placements of grout.
- Cure for minimum seven days by ponding water or with wet hessian cloth.
- Cover top and stray holes / openings of restraint formwork with wet sacks for minimum seven days.